

DIMENSIONES Y PESOS TEÓRICOS DE LAMINAS ASTM A-240 (SERIE 300)

HOJA CALIBRE	ESPESOR		PESO POR HOJA						
	Pulgadas	mm	kg/m ²	3'x8'	3'x10'	4'x8'	4'x10'	5'x10'	6'x10'
10	0.135	3.43	27.783	61.91	77.4	82.569	103.228	129.056	154.86
11	0.12	3.05	24.705	55.051	68.825	73.421	91.792	114.758	137.707
12	0.105	2.67	21.627	48.192	60.25	64.274	80.355	100.458	120.55
14	0.075	1.9	15.39	34.294	42.875	45.738	57.182	71.487	85.785
16	0.06	1.52	12.312	27.435	34.3	36.59	45.745	57.19	
18	0.048	1.22	9.882	22.02	27.53	29.369	36.717	45.902	
20	0.035	0.892	7.225	16.1	20.128	21.473	26.845	33.486	
22	0.029	0.74	5.994	13.357	16.699	17.814	22.271	27.842	
24	0.024	0.61	4.941	11.01	13.765	14.684	18.358	22.951	
26	0.018	0.455	3.686	8.213	10.267	10.953	13.694	17.119	
28	0.015	0.385	3.119	6.949	8.688	9.268	11.587	14.485	
29	0.013	0.33	2.673	5.956	7.447	7.944	9.932	12.416	

DIMENSIONES Y PESOS TEÓRICOS DE LAMINAS ASTM A-240 (SERIE 400)

HOJA CALIBRE	ESPESOR		PESO POR HOJA				
	pulgadas	mm	kg/m ²	3'x8'	3'x10'	4'x8'	4'x10'
10	0.135	3.43	27.097	60.381	75.489	80.53	100.679
11	0.12	3.05	24.095	53.692	67.126	71.608	89.525
12	0.105	2.67	21.093	47.002	58.762	62.687	78.371
14	0.075	1.9	15.01	33.447	41.861	44.609	55.77
16	0.06	1.52	12.008	26.758	33.453	35.687	44.616
18	0.048	1.22	9.638	21.477	26.85	28.643	35.81
20	0.0351	0.892	7.047	15.703	19.631	20.943	26.182
22	0.0291	0.74	5.846	13.027	16.286	17.374	21.721
24	0.024	0.61	4.819	10.738	13.425	14.322	17.905
26	0.018	0.455	3.595	8.01	10.014	10.863	13.355
28	0.015	0.385	3.042	6.777	8.473	9.039	11.301
29	0.013	0.33	2.607	5.809	7.263	7.748	9.686